


A-3 11. (Amended) A thermoformed article obtained from a sheet according to claim 1.

Attached hereto is a marked-up version of the changes made to the claims by the current amendment. Such attachment is captioned "VERSION WITH MARKINGS TO SHOW CHANGES MADE."

Respectfully submitted,



Thomas C. Lagaly
Attorney for Applicants
Registration No. 34,652

Sealed Air Corporation
P.O. Box 464
Duncan, SC 29334
(864) 433-2333

JUNE 26, 2001

Date

09806312-070201

VERSION WITH MARKINGS TO SHOW CHANGES MADE

In the claims:

Claims 1-3, 7-8, and 10-11 have been amended to read as follows, wherein underlined terms have been added and bracketed terms have been deleted:

1. (Amended) A thermoformable, multilayer, co-extruded sheet comprising at least two separate foam polypropylene layers obtained by chemical foaming of two polypropylene resins having different flexural modulus[, a "high modulus" polypropylene and a "low modulus" polypropylene].
2. (Amended) The thermoformable sheet of claim 1 wherein [the] one of the two polypropylene resins is a "low modulus" polypropylene resin [has] having a flexural modulus lower than 1,500 MPa[, preferably \leq 1,400 MPa, and even more preferably \leq 1,300 MPa].
3. (Amended) The thermoformable sheet of claim 1 wherein [the] one of the two polypropylene resins is a "high modulus" polypropylene resin [has] having a flexural modulus \geq 1,500 MPa[, preferably \geq 1,650 MPa, and even more preferably \geq 1,800 MPa].
7. (Amended) The thermoformable[, multilayer, co-extruded] sheet of claim 1 [comprising at least two separate foam polypropylene layers obtained by chemical foaming of two different polypropylene resins having different flexural modulus, a "high modulus" polypropylene and a "low modulus" polypropylene, sandwiching a gas barrier layer comprising a polymer selected from the group consisting of ethylene-vinyl alcohol copolymers (EVOH), vinylidene chloride copolymers (PVDC), polyamides, and blends of

one or more EVOH and one or more polyamides,] wherein the gas barrier layer is bonded to said foam polypropylene layers by means of tie layers of modified polyolefins.

8. (Amended) The thermoformable [multilayer] sheet of claim [7] 3, further comprising a heat-sealing layer adhered [on the] to an outer surface of the "high modulus" polypropylene foamed layer, said heat-sealing layer comprising one or more polymers having a melting point < 140 °C[, and preferably < 130 °C].

10. (Amended) [A] The thermoformable[, multi-layer, co-extruded, polypropylene foam having] sheet of claim 1, wherein said sheet has a density ranging from about 0.50 to about 0.85 g/cm³[, preferably ranging from from about 0.60 to about 0.80 g/cm³] and a flexural modulus higher than 400 MPa.

11. (Amended) A thermoformed article obtained from a sheet according to [any of the preceding claims] claim 1.